VRLA AGM battery ATP HR12-28W-FR




Atlantic Power High Rate series batteries are specially designed for applications that require high power output. With their high-power density and low internal resistance, the HR series are the right choice for your most demanding applications.




Specifications

| Nominal Voltage | 12V | | | |
|--------------------------|-------------------|---------------------|--|--|
| Number of cell | 6 cells | | | |
| Rated capacity(15min.rat | 28 Watts/cell | | | |
| Dimensions | Length | 151±1.5mm(5.94inch) | | |
| | Width | 65±1mm(2.56inch) | | |
| | Height | 94±1mm(3.70inch) | | |
| | Total Height | 100±1mm(3.90inch) | | |
| Approx. Weight | 2.3kg(5.06lbs)±4% | | | |

Outer dimensions (mm)



Terminal Type (mm)



Characteristics

| Capacity(20 | 0H R,25°C) | 7.5Ah | | | | |
|----------------------------|-----------------|---|--|--|--|--|
| Capacity(15m | nin.rate,25°C) | 28 Watts/cell | | | | |
| Termin | al type | T2/T1 | | | | |
| Internal re (Fully char | | Approx.14m Ω | | | | |
| | 40°C | 102% | | | | |
| Capacity affected by | 25°C | 100% | | | | |
| temperature (10HR) | 0°C | 85% | | | | |
| (IOFIK) | -15°C | 65% | | | | |
| | 3 months | Remaining Capacity:91 % | | | | |
| Self-discharge (25°C) | 6 months | Remaining Capacity:82% | | | | |
| (20 0) | 12 months | Remaining Capacity:65% | | | | |
| Nominal operati | ing temperature | 25°C ±3°C(77°F ±5°F) | | | | |
| Operating | Discharge | -15°C-50°C(5°F-122°F) | | | | |
| temperature | Charge | -10°C-50°C(14°F-122°F) | | | | |
| range | Storage | -20°C-50°C(-4°F-122°F) | | | | |
| Float charging | voltage(25°C) | 13.50 to 13.80V Temperature compensation: -18mV/ °C | | | | |
| Cyclic charging | y voltage(25°C) | 14.50 to 15.00V Temperature compensation: -30mV/°C | | | | |
| Maximum cha | arging current | 2.7A | | | | |
| Maximum disc | harge current | 135A(5 sec.) | | | | |
| Designed floa | ting life(20°C) | 5years | | | | |



Construction

| Component | Positive plate | Negative plate | Container | Cover | Separator | Electrolyte | Safety valve | Terminal |
|--------------|----------------|----------------|-----------|-------|-----------|---------------|--------------|----------|
| Raw material | Lead dioxide | Lead | ABS | ABS | AGM | Sulfuric acid | Rubber | Copper |

Constant Current Discharge Characteristics Unit:A(25°C,77°F)


| F.V/Time | 5min | 10min | 15min | 20min | 30min | 45min | 60min | 2h | 3h | 4h | 5h |
|------------|------|-------|-------|-------|-------|-------|-------|------|------|------|------|
| 1.60V/cell | 31.3 | 19.3 | 15.1 | 12.0 | 8.12 | 6.01 | 4.91 | 2.81 | 2.00 | 1.61 | 1.38 |
| 1.67V/cell | 29.9 | 18.4 | 14.6 | 11.5 | 7.85 | 5.81 | 4.80 | 2.79 | 1.98 | 1.58 | 1.37 |
| 1.70V/cell | 29.1 | 17.9 | 14.2 | 11.2 | 7.71 | 5.71 | 4.72 | 2.77 | 1.97 | 1.59 | 1.36 |
| 1.75V/cell | 27.9 | 17.2 | 13.8 | 10.9 | 7.52 | 5.57 | 4.62 | 2.73 | 1.96 | 1.57 | 1.35 |
| 1.80V/cell | 26.3 | 16.1 | 13.0 | 10.3 | 7.25 | 5.36 | 4.48 | 2.66 | 1.91 | 1.53 | 1.32 |

Constant Power Discharge Characteristics Unit:W(25°C,77°F)


| F.V/Time | 5min | 10min | 15min | 20min | 30min | 45min | 60min | 2h | 3h | 4h | 5h |
|------------|-------|-------|-------|-------|-------|-------|-------|------|------|------|------|
| 1.60V/cell | 60.1 | 37.4 | 30.0 | 23.7 | 16.1 | 11.9 | 9.78 | 5.59 | 4.01 | 3.23 | 2.78 |
| 1.67V/cell | 57.38 | 35.7 | 28.9 | 22.8 | 15.6 | 11.5 | 9.52 | 5.54 | 3.98 | 3.20 | 2.75 |
| 1.70V/cell | 55.8 | 34.8 | 28.1 | 22.3 | 15.3 | 14.4 | 9.35 | 5.51 | 3.96 | 3.19 | 2.74 |
| 1.75V/cell | 53.5 | 33.2 | 27.2 | 21.5 | 14.9 | 11.0 | 9.18 | 5.43 | 3.94 | 3.17 | 2.72 |
| 1.80V/cell | 50.5 | 31.5 | 25.8 | 20.4 | 14.4 | 10.6 | 8.84 | 5.29 | 3.82 | 3.07 | 2.64 |

Note: The above characteristics data can be obtained within three charge or discharge cycles.


Discharge characteristics(25°C)




Effect of Temperature on Capacity



Charging characteristics




Self-discharge characteristics






Temperature effects on float life



Cycle service life in relation to depth of discharge



The relationship for OCV and Capacity (25't)

